



Client: Edmund Bell & Co Ltd
Roydsdale Way
Euroway Trading Estate
Bradford
BD4 6SU

Entry No: 44035
Date received: 01/07/2010

Client's Description: Sample of fabric Venus

TEST REPORT

Test Required: Flammability in accordance with IMO A.471 (XII)
Pre-treatment: None
Conditioning: A minimum of 24 hours at 65 +/- 5% Relative Humidity, 20 +/- 5°C
Method of Test: IMO Resolution A563 (14)
Date of Test: 05/07/2010

Flame application time: 5 seconds

Mode of Flame Application: Edge ignition

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Face	Warp direction					Weft direction				
	1	2	3	4	5	1	2	3	4	5
Specimen number										
Flame reached an edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X	X	X	X	X	X	X
Surface Flash (✓ or X)	X	X	X	X	X	X	X	X	X	X
Duration of flaming (s)	7.7	4.0	10.7	0	6.2	1.9	17.9	3.2	24.4	2.3
Length of Char (mm)	70	57	83	45	63	60	75	60	96	57
Ignition of Cotton wool (Y/N)	N	N	N	N	N	N	N	N	N	N

Mean Char Length: Warp = 64 mm Weft = 70 mm

Comments

On the basis of the tests carried out this sample of fabric meets the proposed criteria for curtains and drapes as specified in Appendix 3 of IMO Resolution A 563(14).

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



G Briggs
Head of Laboratory
7th July 2010

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

